JETIR.ORG ISSN: 2349-5162 | ESTD Year : 2014 | Monthly Issue
JOURNAL OF EMERGING TECHNOLOGIES AND INNOVATIVE RESEARCH (JETIR)
An International Scholarly Open Access, Peer-reviewed, Refereed Journal

A Comparative Study of X-Ray Attenuation and Shielding Parameters in Selected Alloys

SATHISH K V
Associate Professor
Department of Physics
Government first Grade College Kolar 563101.

Abstract

X-rays are widely used in medical diagnosis, industrial inspection, scientific research, and imaging applications. The interaction of X-rays with matter depends strongly on photon energy, atomic number, density, and elemental composition. Consequently, the selection of suitable materials for X-ray attenuation requires systematic evaluation of their photon-interaction and shielding parameters. Metallic alloys are particularly interesting because their physical, mechanical, and radiation-interaction properties can be modified by changing their elemental composition. The present article discusses the evaluation of important X-ray attenuation and shielding parameters of selected alloys, including the mass attenuation coefficient, linear attenuation coefficient, half-value layer, tenth-value layer, mean free path, effective atomic number, and effective electron density. The theoretical basis of photon attenuation and the principal photon-interaction mechanisms—photoelectric absorption, coherent scattering, Compton scattering, and pair production—are described. The use of elemental photon-interaction data, such as those provided by the National Institute of Standards and Technology (NIST) XCOM database, provides a reliable approach for estimating attenuation properties of alloys from their compositions. NIST XCOM provides photon cross sections and attenuation coefficients for elements, compounds, and mixtures over a very broad photon-energy range.

Keywords: X-rays, alloys, radiation shielding, mass attenuation coefficient, linear attenuation coefficient, HVL, TVL, mean free path, effective atomic number.

1. Introduction:

X-rays are electromagnetic radiations with wavelengths shorter than those of ultraviolet radiation and are capable of penetrating matter. Their penetrating ability has made them extremely useful in medical imaging, industrial non-destructive testing, security inspection, crystallography and scientific research. Although X-rays are useful, unnecessary exposure to ionizing radiation must be controlled. One important approach to radiation protection is the use of suitable shielding materials. The effectiveness of a material in attenuating X-rays depends on several factors, particularly its elemental composition, density, thickness and the energy of the incident photons. Traditionally, high-density materials containing relatively high-atomic-number elements have attracted considerable attention for photon shielding. However, the choice of a shielding material cannot be based on density alone. Mechanical strength, corrosion resistance, cost, availability, manufacturability and environmental considerations may also influence material selection. Alloys provide an interesting class of materials because their composition can be modified to achieve a combination of

mechanical and radiation-interaction properties. The radiation attenuation characteristics of an alloy can therefore be investigated by considering the contribution of each constituent element.

The NIST XCOM database is an important reference for such investigations. It provides photon cross sections for processes including photoelectric absorption, scattering and pair production, as well as total attenuation coefficients for elements, compounds and mixtures.

NIST data also provide mass attenuation coefficients over photon energies ranging from 1 keV to 20 MeV for elements and selected compounds and mixtures. Therefore, the present article focuses on the theoretical evaluation of X-ray attenuation parameters in selected alloys and discusses how these parameters can be used to assess their potential for X-ray shielding.

2. Interaction of X-Rays with Matter

When an X-ray photon enters an alloy, several interactions may occur. The major photon-interaction mechanisms relevant to attenuation studies are:

2.1 Photoelectric absorption

In the photoelectric effect, an incident photon transfers its energy to a bound electron and is completely absorbed. The electron is ejected from the atom.

Photoelectric absorption is particularly important at relatively low photon energies and generally increases strongly with atomic number.

This makes high-Z elements especially significant in low-energy X-ray attenuation.

2.2 Compton scattering

In Compton scattering, an incident photon interacts with an electron and transfers part of its energy to that electron. The photon continues with reduced energy and a different direction.

Compton scattering becomes increasingly important over intermediate photon-energy ranges.

2.3 Coherent scattering

Coherent or Rayleigh scattering involves interaction of the photon with the atom without significant energy transfer. It contributes to the total attenuation, particularly at lower energies.

2.4 Pair production

At sufficiently high photon energies, a photon can interact in the electromagnetic field of a nucleus and produce an electron–positron pair.

For conventional diagnostic X-ray energies, pair production is generally not the dominant process, but it becomes relevant as photon energy increases.

NIST's photon-interaction database explicitly considers contributions from photoelectric absorption, coherent and incoherent scattering, and pair-production processes when calculating photon attenuation.

3. X-Ray Attenuation Law

The attenuation of a narrow photon beam passing through a material can be represented by the Beer–Lambert law:

I=I0e−μxI=I_0e^{-\mu x}

where:

- I0I_0 = incident photon intensity
- II = transmitted photon intensity
- μ\mu = linear attenuation coefficient
- xx = thickness of absorber.

The linear attenuation coefficient is expressed in units such as cm^{-1}.

Rearranging:

μ=1xln⁡(I0I)\mu=\frac{1}{x}\ln\left(\frac{I_0}{I}\right)

A larger value of μ\mu indicates stronger attenuation for a given material thickness and photon energy.

4. Mass Attenuation Coefficient

The mass attenuation coefficient is defined as:

μρ\frac{\mu}{\rho}

where ρ\rho is the density of the material.

Thus,

μ=(μρ)ρ\mu=\left(\frac{\mu}{\rho}\right)\rho

The mass attenuation coefficient is particularly useful for comparing different materials independently of their physical density.

For an alloy or mixture containing constituent elements ii, a commonly used mixture approximation is:
(μρ)alloy=∑iwi(μρ)i\left(\frac{\mu}{\rho}\right)_{\text{alloy}} = \sum_i w_i \left(\frac{\mu}{\rho}\right)_i
Where wiw_i represents the mass fraction of constituent element ii.
NIST's XCOM methodology allows photon-interaction quantities to be calculated for mixtures from their constituent components.

5. Linear Attenuation Coefficient

The linear attenuation coefficient is calculated from:
μ=ρ(μρ)\mu = \rho\left(\frac{\mu}{\rho}\right)
It directly describes the attenuation per unit thickness.
For shielding applications, this parameter is important because two materials having similar mass attenuation coefficients can provide different attenuation per unit thickness if their densities differ.
Therefore, both **composition and density** must be considered when comparing alloys.

6. Half-Value Layer

The half-value layer (HVL) is the thickness of a material required to reduce the incident photon intensity to one-half of its original value.
Starting with:
II0=e−μx\frac{I}{I_0}=e^{-\mu x}
For I/I0=1/2I/I_0=1/2:
HVL=ln⁡2μ\boxed{HVL=\frac{\ln2}{\mu}}
or
HVL=0.693μ\boxed{HVL=\frac{0.693}{\mu}}
A smaller HVL indicates that less material thickness is required to reduce the photon intensity by 50%.

7. Tenth-Value Layer

The tenth-value layer (TVL) is the thickness required to reduce the photon intensity to one-tenth of its original value.
Thus:
TVL=ln⁡10μ\boxed{TVL=\frac{\ln10}{\mu}}
or
TVL=2.303μ\boxed{TVL=\frac{2.303}{\mu}}
The TVL is useful for evaluating materials intended to provide substantial attenuation.

8. Mean Free Path

The mean free path (MFP) represents the average distance a photon travels before undergoing an interaction.
It is given by:
MFP=1μ\boxed {MFP=\frac{1}{\mu}}
A lower MFP corresponds to stronger attenuation per unit distance.
The relationship among MFP, HVL and TVL is:
HVL=0.693(MFP)HVL=0.693(MFP)
and
TVL=2.303(MFP)TVL=2.303(MFP)

9. Effective Atomic Number

An alloy contains several elements, so it does not have a single atomic number in the same sense as a pure element.
The concept of **effective atomic number (ZeffZ_{\text{eff}})** is therefore used to represent the overall photon-interaction behavior of a compound or mixture.
A general expression based on elemental contributions can be written as:
Zeff=[∑ifiAi∑ifiAi/Zi]Z_{\text{eff}}= \left[\frac{\sum_i f_i A_i} {\sum_i f_i A_i/Z_i} \right]
where the precise weighting factors depend on the interaction process and the methodology used.
The effective atomic number is energy dependent because the relative contributions of photoelectric absorption, Compton scattering and other interactions change with photon energy.
Research on photon attenuation emphasizes that effective atomic number and electron density are derived from the underlying photon-interaction cross sections and attenuation coefficients.

10. Effective Electron Density

The effective electron density describes the number of electrons available per unit mass or volume for photon interaction.

It is particularly useful when comparing materials having different elemental compositions.

Together, ZeffZ_{\text{eff}} and electron density provide additional information beyond the conventional attenuation coefficient and can help explain why attenuation behaviour changes with photon energy.

11. Selected Alloys for Investigation

For a quantitative research study, a representative set of alloys can be selected according to availability and research objectives.

Examples include:

Alloy system	Principal constituents	General significance
Stainless steel	Fe, Cr, Ni and other elements	Strong structural material
Brass	Cu and Zn	Dense engineering alloy
Bronze	Cu and Sn	Copper-based alloy
Aluminum alloy	Al with selected alloying elements	Lightweight engineering material
Nickel alloy	Ni with Cr, Fe and other elements	High-temperature applications

Important: The exact chemical composition should be taken from the manufacturer's specification, certified material composition, experimental characterization, or another reliable source before calculating research results. The table above is therefore a proposed study design rather than experimental data.

12. Methodology

The proposed investigation can be performed through the following steps.

Step 1: Determine alloy composition

The mass fraction of each constituent element is obtained.

For example:

w1+w2+w3+⋯+wn=1w_1+w_2+w_3+\cdots+w_n=1

Step 2: Obtain elemental attenuation coefficients

Mass attenuation coefficients for the constituent elements are obtained at selected photon energies.

The NIST XCOM database is suitable for this purpose because it provides photon cross sections and attenuation coefficients for elements, compounds and mixtures.

Step 3: Calculate alloy mass attenuation coefficient

(μρ)alloy=∑iwi(μρ)i\left(\frac{\mu}{\rho}\right)_{\text{alloy}} = \sum_iw_i \left(\frac{\mu}{\rho}\right)_i

Step 4: Determine density

The density of the alloy is obtained from experimental measurement or a reliable material specification.

Step 5: Calculate linear attenuation coefficient

μ=ρ(μρ)\mu=\rho\left(\frac{\mu}{\rho}\right)

Step 6: Calculate shielding parameters

HVL=0.693μHVL=\frac{0.693}{\mu} TVL=2.303μTVL=\frac{2.303}{\mu} MFP=1μMFP=\frac{1}{\mu}

Step 7: Calculate ZeffZ_{\text{eff}} and electron density

These parameters are calculated using an appropriate established methodology based on the elemental composition and photon-interaction cross sections.

13. Suggested Photon-Energy Range

The study can investigate several photon energies, for example:

20, 30, 40, 60, 80, 100, 150, 200, 300, 500 and 1000 keV

The exact energies should be selected according to the intended application.

For medical X-ray applications, lower-energy X-ray ranges may be particularly relevant, whereas industrial and broader photon-shielding studies can consider a wider energy range.

NIST's mass attenuation coefficient tables cover photon energies from 1 keV to 20 MeV, making them suitable as a reference framework for a wide energy range.

14. Results and Discussion

The expected results should be presented in tables containing:

Photon energy	Alloy	μ/ρ	μ	HVL	TVL	MFP	ZeffZ_{\text{eff}}
20 keV	Alloy A	—	—	—	—	—	—
20 keV	Alloy B	—	—	—	—	—	—
20 keV	Alloy C	—	—	—	—	—	—
50 keV	Alloy A	—	—	—	—	—	—
50 keV	Alloy B	—	—	—	—	—	—
50 keV	Alloy C	—	—	—	—	—	—
100 keV	Alloy A	—	—	—	—	—	—
100 keV	Alloy B	—	—	—	—	—	—

The blank values should be populated only after the actual alloy compositions and density values are established.

Expected trends

The mass attenuation coefficient generally decreases as photon energy increases, although absorption edges can produce abrupt changes. NIST's attenuation data demonstrate that photon attenuation depends strongly on energy and elemental composition.

At lower photon energies, the photoelectric effect can make a major contribution to attenuation. As photon energy increases, Compton scattering becomes increasingly important. At sufficiently high energies, pair production becomes relevant.

Consequently, an alloy with a larger contribution from higher-Z elements may show enhanced attenuation in certain energy ranges, while density strongly affects its linear attenuation coefficient.

15. Relationship Between Density and Shielding

Density is an important factor in determining the practical shielding performance of an alloy.

Consider two materials with approximately similar mass attenuation coefficients:

(μρ)A≈(μρ)B\left(\frac{\mu}{\rho}\right)_A \approx \left(\frac{\mu}{\rho}\right)_B

If:

ρA>ρB\rho_A>\rho_B

then:

μA>μB\mu_A>\mu_B

because:

μ=ρ(μρ)\mu=\rho\left(\frac{\mu}{\rho}\right)

Therefore, the denser alloy will generally have a smaller HVL:

HVL=0.693μHVL=\frac{0.693}{\mu}

This illustrates why both mass attenuation and density must be considered when selecting an alloy for a specific shielding application.

16. Importance of Alloy Composition

Changing the elemental composition of an alloy changes its photon-interaction behaviour.

For example, adding an element with a comparatively high atomic number may alter the photoelectric contribution, while changing the proportion of lighter elements may influence the overall effective atomic number and electron density.

Thus, alloy design can potentially be used to balance:

- Radiation attenuation
- Mechanical strength
- Density
- Corrosion resistance
- Thermal stability
- Cost
- Manufacturability

Reviews of metallic alloys for photon shielding have specifically considered parameters such as mass attenuation coefficient, effective atomic number, electron density, mean free path, HVL and TVL.

17. Potential Applications

The study of X-ray attenuation parameters of alloys has several potential applications.

17.1 Medical imaging

X-ray attenuation data are important when designing or evaluating shielding materials used around diagnostic imaging facilities.

17.2 Industrial radiography

Industrial inspection uses penetrating radiation to examine internal features of components. Appropriate shielding is necessary to control radiation exposure.

17.3 Scientific laboratories

Research facilities using X-ray-generating equipment require appropriate radiation-control measures.

17.4 Aerospace and engineering

Material selection for radiation environments can require simultaneous consideration of mechanical and photon-interaction properties.

17.5 Radiation-protection structures

Alloys may provide useful combinations of structural strength and photon attenuation, potentially allowing shielding components to perform both structural and radiation-protection functions.

18. Advantages of Studying Alloys

Compared with studying individual pure elements, alloy research offers several advantages.

1. **Tailored composition:** alloy composition can be modified.
2. **Mechanical strength:** many alloys have substantially better engineering properties than pure metals.
3. **Corrosion resistance:** appropriate alloying can improve durability.
4. **Manufacturing flexibility:** alloys can be produced in sheets, plates and structural components.
5. **Multifunctionality:** one material can potentially provide structural and shielding functions.
6. **Cost optimization:** expensive elements can potentially be reduced while retaining useful attenuation characteristics.

19. Limitations

Theoretical attenuation calculations should not automatically be interpreted as experimental measurements.
Several factors can influence actual attenuation:

- Exact alloy composition
- Density variations
- Porosity
- Manufacturing process
- Material thickness
- Surface condition
- Photon-energy spectrum
- Beam geometry
- Scattered radiation
- Experimental uncertainties

Therefore, theoretical values obtained from elemental databases should ideally be validated through experimental transmission measurements when the study is intended for publication as an experimental research paper.

NIST also notes that different photon databases can use different calculation approaches, so the selected database and methodology should be stated clearly in a research paper.

20. Conclusion:

The attenuation of X-rays in metallic alloys is governed by photon energy, elemental composition and material density. Parameters such as the mass attenuation coefficient, linear attenuation coefficient, HVL, TVL, MFP, effective atomic number and effective electron density provide complementary information about the interaction of X-rays with alloys. The mass attenuation coefficient provides a useful composition-dependent measure of photon attenuation, while the linear attenuation coefficient additionally incorporates material density. HVL and TVL provide practical measures of the thickness required to achieve specified levels of attenuation. The effective atomic number and electron density provide further insight into the energy-dependent

interaction behavior of multicomponent alloys. NIST XCOM provides an established computational framework for obtaining photon cross sections and attenuation coefficients for elements, compounds and mixtures over a wide energy range. The proposed comparative study of selected alloys can therefore provide useful information for understanding their X-ray attenuation characteristics and assessing their potential suitability for applications involving radiation protection and controlled X-ray transmission. However, numerical results should be generated from the **actual chemical composition and density of the selected alloys**, and experimental validation should be performed wherever possible.

References:

1. Berger, M. J., Hubbell, J. H., Seltzer, S. M., Chang, J., Coursey, J. S., Sukumar, R., Zucker, D. S., & Olsen, K. (2010). *XCOM: Photon Cross Section Database, Version 1.5*. National Institute of Standards and Technology.
2. Hubbell, J. H., & Seltzer, S. M. (1995). *Tables of X-Ray Mass Attenuation Coefficients and Mass Energy-Absorption Coefficients 1 keV to 20 MeV for Elements Z = 1 to 92 and 48 Additional Substances of Dosimetry Interest*. NISTIR 5632.
3. Berger, M. J., & Hubbell, J. H. (1987). *XCOM: Photon Cross Sections on a Personal Computer*. NBSIR 87-3597, National Bureau of Standards.
4. Seltzer, S. M., & Hubbell, J. H. (1995). Tables and graphs of photon mass attenuation coefficients and mass energy-absorption coefficients. *Publication of the Japanese Society of Radiological Technology*.
5. Hubbell, J. H. (1969). *Photon Cross Sections, Attenuation Coefficients, and Energy Absorption Coefficients from 10 keV to 100 GeV*. NBS NSRDS 29.
6. Saloman, E. B., & Hubbell, J. H. (1986). *X-Ray Attenuation Coefficients (Total Cross Sections): Comparison of Experimental Database with Recommended Values*. NBSIR 86-3431.
7. NIST. *X-Ray and Gamma-Ray Data*. National Institute of Standards and Technology.
8. NIST. *X-Ray Mass Attenuation Coefficients, Standard Reference Database 126*.
9. *Review on scope of metallic alloys in gamma rays shield designing*. *Progress in Nuclear Energy*, 113, 95–113 (2019).